

Bureau of Research, Testing and Consultation (BRTC)
 To check authenticity of this report, please scan the QR Code.
 Alternatively, please visit <http://brtc.mme.buet.ac.bd>.

Department of Materials and Metallurgical Engineering (MME)
 Bangladesh University of Engineering and Technology (BUET)



Client: Mr. Md. Golam Mowla
 QC Manager
 Shahriar Steel Mills Limited
 Konapara, Jatrabari
 Dhaka 1362

Client's Reference: Nil; Date 05/11/2019
 BRTC Reference: 1101-99456/MME/2019-20; Date 05/11/2019
 Sample Condition: Not Sealed

Date: 24 November 2019
 MME No: 0473(09)/2019-20

TEST OF DEFORMED M.S. REBAR (ASTM A615M-16)

Frog Mark/ Description	Sample No.	Bar	Actual Dia	Unit Weight	Average Unit Weight	Yield Load	Yield Strength	Average Yield Strength	Tensile Load	Tensile Strength	Average Tensile Strength	TS/YS Ratio	Elongation (GI 200 mm)	Average Elongation	Bend Test (Separate Samples)
		Designation / Nominal Dia													
SSRM RB 400 20	1	20	19.99	2.464	2.480	141.50	450	446	222.59	709	707	1.58	18	18	Satisfactory
	2	20	20.08	2.485		142.35	453	446	222.54	708	707	1.56	18		Satisfactory
	3	20	20.09	2.489		136.40	434	(64500)	220.71	703	(102500)	1.62	18		Satisfactory

* TS/YS ratio is not required as per ASTM A615M.
 * Strength values are calculated based on nominal area.

Weight Requirements for Steel Rebar (As Per ASTM A615/A615M-16 Table A1.1)

Bar Designation Number/Nominal Dia., mm	10	12	16	20	25	28	32	36	40	50	60
Nominal Weight, kg/m	0.617	0.888	1.578	2.466	3.853	4.834	6.313	7.990	9.865	15.410	22.200

* Measured unit weight shall not be less than 94% of the nominal weight.

Minimum Tensile Requirements for Steel Rebar (As Per ASTM A615/A615M-16 Table A1.2)

Grade	ASTM A615			ASTM A615M			Minimum Elongation in 8 in. (200 mm) Gauge Length, per cent											
	Yield Strength psi (MPa)	Tensile Strength psi (MPa)	Grade	Yield Strength MPa (psi)	Tensile Strength MPa (psi)	Grade (A615M)	Bar Designation Number											
40	40,000 (280)	60,000 (420)	280	280 (40,000)	420 (60,000)	10	10	12	16	20	25	28	32	36	40	50	60	
60	60,000 (420)	90,000 (620)	420	420 (60,000)	620 (90,000)	11	11	12	12	12	-	-	-	-	-	-	-	
75	75,000 (520)	100,000 (690)	520	520 (75,000)	690 (100,000)	7	7	7	7	7	7	7	7	7	7	6	6	
80	80,000 (550)	105,000 (725)	550	550 (80,000)	725 (105,000)	7	7	7	7	7	7	7	7	7	7	6	6	
100	100,000 (690)	115,000 (790)	690	690 (100,000)	790 (115,000)	7	7	7	7	7	7	7	7	7	7	6	6	



op5pizujit

Falwida 24.11.19
 Dr. Fahmida Gulshan
 Professor and Head

Please note: The client supplied the sample(s) and the result given herewith corresponds to the sample(s) tested only. Department of MME, BUET takes no responsibility regarding the misidentification, if any, of the sample(s).

005829

Department of MME, Old Academic Building, 1st Floor, BUET, Dhaka 1000 +880 1741 362 504 +880 2 5516 7228-57 Ext 7629 brcmme@mme.buet.ac.bd